

Silver Plated Copper Conductive Elastomer

The following is a relative measurement of the resistance and shielding effectiveness properties for silver plated copper conductive elastomer, tested in accordance with the procedures and requirements outlined in United States military specification MIL-DTL-83528, Type A.

Electrical Specifications	Tolerance	Test Method	Silver Plated Copper Elastomer (Ohm-cm)
Volume Resistivity	Maximum	MIL-DTL-83528 (PARA 4.6.11)	0.004
Shielding Effectiveness (Frequencies)	Minimum	MIL-DTL-83528	Silver Aluminum Elastomer (dB)
100 MHz (E-Field)	Minimum	MIL-DTL-83528	120
500 MHz (E-Field)	Minimum	MIL-DTL-83528	120
2 GHz (Plane Wave)	Minimum	MIL-DTL-83528	120
10 GHz (Plane Wave)	Minimum	MIL-DTL-83528	120

Properties (General Specifications for Silver Plated Aluminum Elastomer)					
Hardness (Shore A)	Tensile (psi)	Elongation (min. – max.)	Tear (lb./in)	Volume Resistivity (ohm-cm)	Specific Gravity (g/cc)
65	200	100 - 300	25	0.004	3.5

This material adheres to the MIL-DTL 83528 specification.

Application: The surface that this material is to be applied to must be conductive, meaning no non-conductive paint, oils, or coatings. If a non-conductive surface is present on the mating or mounting surface the conductive elastomer, shielding effectiveness will be greatly degraded.

MAJR PRODUCTS CORPORATION

780 South Street
Saegertown, PA 16433
www.majr.com

(814) 763-3211
(814) 763-2952 Fax
e-mail: sales@majr.com